

## Enviro Klean<sup>®</sup> Safety Peel 1 Paint Stripper Specification

*Specifier Note: The information provided below is intended to guide the Architect in developing specifications for products manufactured by PROSOCO, Inc. and should not be viewed as a complete source of information about the product(s). The Architect should always refer to the Product Data Sheet and MSDS for additional recommendations and for safety information*

*Specifier Note: Paragraph below is for PART 1 GENERAL, Quality Assurance.*

### Test Area

Test a minimum 4 ft. by 4 ft. area on each type of masonry. Use manufacturer's application instructions. Let the test panel dry 3 to 7 days before inspection. Keep test panels available for comparison throughout the cleaning project.

*Specifier Note: Paragraphs below are for PART 2 PRODUCTS, Manufacturers and Products.*

**Manufacturer:** PROSOCO, Inc., 3741 Greenway Circle, Lawrence, KS 66046. Phone: (800) 255-4255; Fax: (785) 830-9797. E-mail: [CustomerCare@prosoco.com](mailto:CustomerCare@prosoco.com)

### Product Description

Enviro Klean<sup>®</sup> Safety Peel 1 is a solvent paste designed for removal of paint, graffiti and clear coatings that contains no methylene chloride or methanol. Safety Peel 1 is a "slow-working" paint remover with a mild citrus odor. Usually just one application dissolves multiple layers.

Safety Peel 1 reduces environmental and applicator risks associated with use of conventional chemical paint removers. Used properly, Safety Peel 1 substantially reduces the volume of waste. Potentially hazardous paint solids are trapped in the semi-dry paste, which is then "peeled" from the surface, simplifying containment and disposal.

### Technical Data

FORM: Light Green Paste

SPECIFIC GRAVITY: 1.24

TOTAL SOLIDS: N/A

pH: N/A

WT./GAL.: 10.3 lbs.

FLASH POINT: 157 degrees F (69 degrees C) ASTM D 3278

FREEZE POINT: < -22 degrees F (< -30 degrees C)

### Limitations

- May not be effective for removal of some paints. When Safety Peel 1 is not effective, test Safety Peel 2 or 3 or other PROSOCO stripper.

*Specifier Note: Paragraphs below are for PART 3 EXECUTION, Installation.*

### Application

Before applying, read "Preparation" and "Safety Information" sections in the Manufacturer's Product Data Sheet for Safety Peel 1. Do not dilute or alter.

1. Apply with a brush, roller or trowel, 1/16" to 1/8" thick.
2. Cover Safety Peel 1 with sheets of Enviro Klean<sup>®</sup> OverCoat<sup>™</sup>, printed side outward. Rub gently to remove air pockets and ensure smooth, overall adhesion..
3. Let Safety Peel 1 and OverCoat<sup>™</sup> dwell at least two hours before evaluating their effectiveness. Some types and thicknesses of coatings may need dwell times of up to 24 hours. Multiple applications may also be necessary.

4. Remove and collect the paste, paper and dissolved material by inserting a trowel, spatula or other paint scraping tool through the paste and lifting it from the surface. Remove as much as possible. Reapply as needed.
5. Rinse surface clean with water, preferably heated water, to improve removal effectiveness. Let cleaned surface dry thoroughly before any other treatment is applied. If residual product has dried on the surface, wet it down with warm water and keep it moist for 15 minutes. This makes it easier to rinse thoroughly with a pressure washer.
6. Dispose of paper, spent cleaner and dissolved coatings/contaminants according to local, state and federal regulations.

*Specifier Note: If the waste generated through paint stripping operations is classified as "hazardous", contractors must consult and comply with current federal, state and local regulations regarding containment, transport and disposal of hazardous waste. See also "Waste Disposal" and "Lead-Based Paint Removal" sections of the manufacturer's product data sheet.*